

# CoolPoly® E1201

Polypropylene  
Celanese Corporation

Message:

CoolPoly E series of thermally conductive plastics transfers heat, a characteristic previously unavailable in injection molding grade polymers. CoolPoly is lightweight, netshape moldable and allows design freedom in applications previously restricted to metals. The E series is electrically conductive and provides inherent EMI/RFI shielding characteristics.

| General Information  |                                 |                   |             |
|--|---------------------------------|-------------------|-------------|
| Features   | Conductivity                    |                   |             |
|  | Heat conduction                 |                   |             |
|  | Electromagnetic shielding (EMI) |                   |             |
|  | Good formability                |                   |             |
|  | Radio frequency shielding (RFI) |                   |             |
| RoHS Compliance  | RoHS compliance                 |                   |             |
| Forms  | Particle                        |                   |             |
| Processing Method  | Injection molding               |                   |             |
| Physical   | Nominal Value                   | Unit              | Test Method |
| Density  | 1.24                            | g/cm <sup>3</sup> | ISO 1183    |
| Molding Shrinkage  |                                 |                   | ASTM D955   |
| Flow   | 0.35                            | %                 | ASTM D955   |
| Transverse flow  | 0.60                            | %                 | ASTM D955   |
| Mechanical   | Nominal Value                   | Unit              | Test Method |
| Tensile Modulus  | 5620                            | MPa               | ISO 527-2   |
| Tensile Stress (Yield)   | 22.0                            | MPa               | ISO 527-2   |
| Nominal Tensile Strain at Break  | 1.0                             | %                 | ISO 527-2   |
| Flexural Modulus   | 5410                            | MPa               | ISO 178     |
| Flexural Stress  | 37.0                            | MPa               | ISO 178     |
| Impact   | Nominal Value                   | Unit              | Test Method |
| Charpy Notched Impact Strength   | 3.3                             | kJ/m <sup>2</sup> | ISO 179     |
| Charpy Unnotched Impact Strength   | 5.4                             | kJ/m <sup>2</sup> | ISO 179     |
| Thermal  | Nominal Value                   | Unit              | Test Method |
| Specific Heat  | 1280                            | J/kg/°C           | ASTM C351   |
| Thermal Conductivity   | 10                              | W/m/K             | ASTM C177   |
| Additional Information   |                                 |                   |             |
| The value listed as Thermal Conductivity, ASTM C177, was tested in accordance with ASTM E1461. The value listed as Mold Shrinkage, ASTM D955, was tested in accordance with ASTM D551. The value listed as Specific Heat ASTM C351, was tested in accordance with ASTM E1461. Thermal Diffusivity, ASTM E1461: 0.0587 cm <sup>2</sup> /sec |                                 |                   |             |
| Injection  | Nominal Value                   | Unit              |             |
| Drying Temperature   | 80.0                            | °C                |             |

|                         |               |     |
|-------------------------|---------------|-----|
| Drying Time             | 1.0 - 2.0     | hr  |
| Dew Point               | -20.0         | °C  |
| Rear Temperature        | 190 - 220     | °C  |
| Middle Temperature      | 210 - 230     | °C  |
| Front Temperature       | 215 - 245     | °C  |
| Processing (Melt) Temp  | 215 - 245     | °C  |
| Mold Temperature        | 20.0 - 65.0   | °C  |
| Injection Pressure      | 35.0 - 105    | MPa |
| Injection Rate          | Moderate-Fast |     |
| Holding Pressure        | 20.0 - 55.0   | MPa |
| Back Pressure           | 0.00 - 0.350  | MPa |
| Screw Speed             | 20 - 60       | rpm |
| Screw Compression Ratio | 2.0:1.0       |     |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

