

Lumax® HR5157

Acrylonitrile Butadiene Styrene + PBT

LG Chem Ltd.

Message:

Description

Heat Resistance

Application

E&E(CD ROM Tray)

General Information			
UL YellowCard	E67171-248438		
Features	High Heat Resistance		
Uses	Electrical/Electronic Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.33	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 to 0.90	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.080	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break, 3.20 mm)	69.6	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	3.0	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	4120	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 3.20 mm)	108	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.40 mm)	64	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	175	°C	ASTM D648
Peak Melting Temperature	223	°C	ASTM D3418
RTI Elec	50.0	°C	UL 746
RTI Imp	50.0	°C	UL 746
RTI Str	50.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Dielectric Strength (1.00 mm)	21	kV/mm	ASTM D149
Arc Resistance	PLC 5		ASTM D495
Comparative Tracking Index (CTI) ⁵	PLC 2		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	HB		

3.00 mm	HB	
Injection	Nominal Value	Unit
Drying Temperature	100	°C
Drying Time	4.0 to 5.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	225 to 235	°C
Middle Temperature	230 to 245	°C
Front Temperature	245 to 255	°C
Nozzle Temperature	245 to 255	°C
Processing (Melt) Temp	245 to 255	°C
Mold Temperature	40.0 to 80.0	°C

NOTE

- | | |
|----|------------|
| 1. | 5.0 mm/min |
| 2. | 5.0 mm/min |
| 3. | 1.3 mm/min |
| 4. | 1.3 mm/min |
| 5. | Solution A |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT