

KOPLA PP KPT1030

Polypropylene

KOPLA Co., Ltd.

Message:

KOPLA PP KPT1030 is a Polypropylene material filled with mineral. It is available in Asia Pacific.

Important attributes of KOPLA PP KPT1030 are:

Flame Rated

Good Dimensional Stability

Warp Resistant

Typical application of KOPLA PP KPT1030: Automotive

General Information			
Filler / Reinforcement	Mineral		
Features	Good Dimensional Stability		
	Low Warpage		
Uses	Automotive Instrument Panel		
	Automotive Under the Hood		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.70 to 1.1	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	98		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	37.3	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	20	%	ASTM D638
Flexural Modulus (23°C)	35000	MPa	ASTM D790
Flexural Strength (23°C)	56.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	44	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	145	°C	
1.8 MPa, Unannealed	95.0	°C	
Melting Temperature	163	°C	
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

