

CONAP® EN-5852

Polyurethane
Cyttec Industries Inc.

Message:

CONAP EN-5852 is a filled, flame-retardant, two-component polyurethane system formulated for potting and encapsulating electrical and electronic components, modules, circuit boards, assemblies, and related devices.

General Information			
Features	Filled		
	Flame Retardant		
	Good Electrical Properties		
	Low Temperature Flexibility		
Uses	Electrical Parts		
	Electrical/Electronic Applications		
	Printed Circuit Boards		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
	Brown		
Processing Method	Encapsulating		
	Potting		
Physical	Nominal Value	Unit	
Specific Gravity			
-- 1	1.21	g/cm ³	
-- 2	1.45	g/cm ³	
Hardness	Nominal Value	Unit	
Durometer Hardness (Shore A)	85		
Elastomers	Nominal Value	Unit	
Tensile Strength	5.93	MPa	
Tensile Elongation (Break)	180	%	
Tear Strength	28.0	kN/m	
Thermal	Nominal Value	Unit	
Glass Transition Temperature	-44.0	°C	
Thermal Conductivity	0.60	W/m/K	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	4.2E+15	ohms	
Volume Resistivity (25°C)	1.1E+15	ohms · cm	

Dielectric Strength (1.59 mm)	18	kV/mm	
Dielectric Constant (25°C, 1 kHz)	4.34		
Dissipation Factor (25°C, 1 kHz)	0.087		
Flammability	Nominal Value	Unit	Test Method
Flame Rating (2.80 mm)	V-0		UL 94
Thermoset	Nominal Value	Unit	
Thermoset Components			
Hardener	Mix Ratio by Weight: 100		
Resin	Mix Ratio by Weight: 20		
Thermoset Mix Viscosity (25°C)	8500	cP	
NOTE			
1.	Resin		
2.	Hardener		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT