Polyrocks 7001B

Acrylonitrile Butadiene Styrene

Polyrocks Chemical Co., Ltd

Message:

7001(+) is environmental flame retardant ABS with environmental bromine-antimony flame retardant system. Adopting the advanced processing technology to ensure flame ratardant effect and have good rigidity and toughness. Environmental flame retardant ABS has passed SGS, CTI tests, and meets the requirements of RoHS, SVHC, PFOS & PFOA, 16P, PAHs...etc.

Flame retardant ABS7001B: good toughness and excellent flowability.

Application: shells of electronic appliances, skeleton, automotive interior decorative panels, dashboard...etc.

General Information				
Additive	Flame retardancy 2			
Features	Good Rigidity			
	High liquidity			
	Good toughness			
	Flame retardancy			
Uses	Electrical/Electronic Applications			
	Home appliance components			
	Car interior equipment			
	Car dashboard			
Agency Ratings	EC 1907/2006 (REACH)			
RoHS Compliance	RoHS compliance			
Forms	Particles			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.18	g/cm³	ASTM D792	
Melt Mass-Flow Rate (MFR)	65	g/10 min	ASTM D1238	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength	40.0	MPa	ASTM D638	
Tensile Elongation (Break)	40	%	ASTM D638	
Flexural Modulus	2300	MPa	ASTM D790	
Flexural Strength	55.0	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact	200	J/m	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load (0.45				
MPa, Unannealed)	90.0	°C	ASTM D648	
Flammability	Nominal Value	Unit	Test Method	
Flame Rating			UL 94	
1.5 mm	V-0		UL 94	
2.0 mm	V-0		UL 94	

3.0 mm	5VA		UL 94
Glow Wire Flammability Index	850	°C	IEC 60695-2-12

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

