

Hifax RTA3263/2

Thermoplastic Polyolefin Elastomer
LyondellBasell Industries

Message:

Hifax RTA3263/2 medium melt flow, 1,700 MPa flexural modulus, paintable, mineral-filled thermoplastic elastomeric olefin (TEO) resin has a very good combination of rigidity, impact strength and paintability. It was designed primarily for rigid automotive exterior ornamentation applications.

General Information			
Filler / Reinforcement	Mineral		
Features	Good Dimensional Stability		
	Good Impact Resistance		
	Good Stiffness		
	Medium Flow		
	Paintable		
Uses	Automotive Applications		
	Automotive Exterior Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.08	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ASTM D1238, ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	20.0	MPa	ISO 527-2
Tensile Strain (Yield)	10	%	ISO 527-2
Flexural Modulus	1700	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180
-40°C	3.3	kJ/m ²	
23°C	21	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	100	°C	ISO 75-2/B
1.8 MPa, Unannealed	56.0	°C	ISO 75-2/A
CLTE - Flow (-30 to 100°C)	6.0E-5	cm/cm/°C	ASTM E228, ISO 11359-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

