

Jackdaw PP ER34NT6552

Polypropylene
Jackdaw Polymers

Message:

Jackdaw PP ER34NT6552 is a Polypropylene product filled with 20% glass fiber. It is available in Europe. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm³	ASTM D792, ISO 1183
Molding Shrinkage	0.30	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	85.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	4.0	%	ASTM D638, ISO 527-2
Flexural Modulus	5000	MPa	ASTM D790, ISO 178
Flexural Stress			
--	130	MPa	ISO 178
Break	130	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	9.0	kJ/m²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	135	°C	ASTM D648, ISO 75-2/A
Peak Melting Temperature	175	°C	ASTM D2117, ISO 1218
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT