

Next Nylon 6 Prime Series NG40-01NC

Polyamide 6

Next Polymers Ltd.

Message:

Description

PA6 Glass Fiber Reinforced Natural compound

Product Applications

This product was developed for the application on parts where good mechanical property, superficial aspect and dimensional stability are required.

Benefits

Good Thermal resistance, Excellent dimensional stability and High strength

General Information				
Filler / Reinforcement		Glass Fiber,40% Filler by Weight		
Features		Good Dimensional Stability		
		Pleasing Surface Appearance		
Uses		Engineering Parts		
Agency Ratings		EC 1907/2006 (REACH)		
RoHS Compliance		RoHS Compliant		
Appearance		Natural Color		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.45	--	g/cm ³	ASTM D792
Molding Shrinkage				ASTM D955
Flow	0.39	--	%	
Across Flow	0.88	--	%	
Water Absorption				ASTM D570
23°C, 24 hr	1.4	--	%	
Saturation ¹	4.5	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ASTM D785
M-Scale	120	--		
R-Scale	130	--		
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength	195	135	MPa	ASTM D638
Tensile Elongation (Break)	4.0	7.0	%	ASTM D638
Flexural Modulus	11500	7500	MPa	ASTM D790
Flexural Strength	260	--	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact (23°C)	180	250	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method

Deflection Temperature Under Load				ASTM D648
0.45 MPa, Unannealed	220	--	°C	
1.8 MPa, Unannealed	210	--	°C	
Melting Temperature	220	--	°C	ASTM D2117
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+13	ohms·cm	IEC 60093
Electric Strength	25	20	kV/mm	IEC 60243-1
Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.800 mm)	HB	--		UL 94
Injection	Dry	Unit		
Drying Temperature - Hot Air Dryer	80.0		°C	
Drying Time	4.0 to 6.0		hr	
Suggested Max Moisture	0.20		%	
Rear Temperature	230 to 240		°C	
Middle Temperature	250 to 260		°C	
Front Temperature	260 to 270		°C	
Mold Temperature	65.0 to 85.0		°C	
NOTE				
1.	Immersed			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

