

PRIME TPO J-5900

Polypropylene Homopolymer
Prime Polymer Co., Ltd.

Message:

PRIME TPO J-5900 is a Polypropylene Homopolymer (PP Homopolymer) product. It is available in Asia Pacific, Europe, or North America.

General Information			
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	67		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
Yield	17.5	MPa	
Break	21.5	MPa	
Tensile Strain (Break)	< 500	%	ISO 527-2
Flexural Modulus	420	MPa	ISO 178
Flexural Stress	17.0	MPa	ISO 178
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	80	μm	
Tensile Modulus			JIS Z1702
MD : 80 μm	430	MPa	
TD : 80 μm	430	MPa	
Tensile Stress			JIS Z1702
MD : Break, 80 μm	40.0	MPa	
TD : Break, 80 μm	40.0	MPa	
Tensile Elongation			JIS Z1702
MD : Break, 80 μm	< 500	%	
TD : Break, 80 μm	< 500	%	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	15	kJ/m ²	ISO 180
Optical	Nominal Value	Unit	Test Method
Haze			JIS K7105
80.0 μm ¹	0.60	%	
80.0 μm ²	4.0	%	
NOTE			
1.	Internal		
2.	All		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

