

# ROPOTEN® T FV-20-205

Low Density Polyethylene

LUKOIL Bulgaria Ltd.

## Message:

Grades FV-03-223, FV-15-204, FV-20-205, FV-20-205-3 are used for production of heavy duty industrial bags, for blow-moulded bottles, for agricultural film, film for building and machine-building applications, for production of toys, souvenirs, for production of thin film for small packages, etc.

General Information			
Uses	Packaging		
	Films		
	Industrial application		
	Architectural application field		
	Agricultural application		
	Bottle		
	Toys		
	Heavy packing bag		
Appearance	Natural color		
Forms	Particles		
Physical	Nominal Value	Unit	Test Method
Density	0.919	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.8 - 2.6	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 9.50	MPa	ASTM D638
Tensile Elongation (Break)	> 500	%	ASTM D638
Optical	Nominal Value	Unit	Test Method
Haze	11	%	ASTM D1003
Additional Information	Nominal Value	Unit	Test Method
Impurities <sup>1</sup>	10 peices (max)		Internal method
Volatiles	0.070	%	Internal method
Non-melting material: <15 pieces, BDS 1008682Off-spec granules: 1.7%, BDS 1008682			
NOTE			
1.	In 200 g sample		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

