

INEOS HDPE K44-15-122

High Density Polyethylene Copolymer

INEOS Olefins & Polymers USA

Message:

K44-15-122 is a natural high-density polyethylene copolymer designed specifically for extrusion of pipe. It has NSF Standard 14 certification for potable water applications, complies with ANSI/NSF Standard 61 health effects requirements, and is recognized by the Plastic Pipe Institute as having a pipe material designation code of PE 3608 (formerly PE 3408). A pressure rated formulation is also produced when this product is extruded in combination with an INEOS-approved black masterbatch. The resulting formulation known as K44-15-123 has NSF Standard 14 certification and complies with ANSI/NSF Standard 61 health effects requirements, is certified to CSA Standard B137.1-05 and B137.4-05, and is listed with the Plastic Pipe Institute as having a PE 3608 (formerly PE3408) and PE80 pipe material designation code.

General Information			
Features	Copolymer		
	High Density		
Uses	Piping		
	Potable Water Applications		
Agency Ratings	EC 1907/2006 (REACH)		
	NSF 14		
	NSF 61		
	PPI PE-3608		
RoHS Compliance	Contact Manufacturer		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Pipe Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.944	g/cm ³	ASTM D4883
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/21.6 kg	12	g/10 min	
190°C/5.0 kg	0.52	g/10 min	
Environmental Stress-Cracking Resistance (100% Igepal, F50)	> 1000	hr	ASTM D1693B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	67		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Yield	20.7	MPa	
Break	34.5	MPa	
Tensile Elongation ²			ASTM D638
Yield	11	%	

Break	> 800	%	
Flexural Modulus - 2% Secant	752	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	480	J/m	ASTM D256
Notched Izod Impact (Area)	45.0	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -118	°C	ASTM D746
Vicat Softening Temperature	121	°C	ASTM D1525
Oxidation Induction Time (210°C)	> 35	min	ASTM D3895
Thermal Stability	127	°C	ASTM D3350
Cell Classification	335464A		ASTM D3350
PENT - Notch Tensile	> 100	hr	ASTM F1473
NOTE			
1.	51 mm/min		
2.	51 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

