

RONFALIN® MABS 2224

Methyl Methacrylate / ABS

A. Schulman Europe

Message:

good flow high impact MABS grade

General Information			
Processing Method	Injection molding		
Resin ID (ISO 1043)	MABS		
Physical	Nominal Value	Unit	Test Method
Density	1.09	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	24.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1700	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	41.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	3.5	%	ISO 527-2/1A/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	13	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	88	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	73.0	°C	ISO 75-2/Af
Vicat Softening Temperature	93.0	°C	ISO 306/B50
Flammability	Nominal Value	Test Method	
Flammability Classification (1.5 mm)	HB	IEC 60695-11-10, -20	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT