

Novodur® M201AS

Acrylonitrile Butadiene Styrene

Styrolution

Message:

Novodur M201AS is a medium impact, high gloss injection molding grade with improved chemical resistance

General Information			
Features	High Gloss		
	Medium Impact Resistance		
Uses	Appliances		
	Household Goods		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	18.0	cm ³ /10min	ISO 1133
Molding Shrinkage	0.40 to 0.70	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	105	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2400	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	47.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield, 23°C	2.5	%	
Break, 23°C	> 15	%	
Flexural Modulus	2300	MPa	ISO 178
Flexural Stress	70.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	10	kJ/m ²	
23°C	19	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-30°C	80	kJ/m ²	
23°C	140	kJ/m ²	
Notched Izod Impact Strength			ISO 180/A
-30°C	10	kJ/m ²	
23°C	20	kJ/m ²	

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Annealed	100	°C	ISO 75-2/B
1.8 MPa, Annealed	96.0	°C	ISO 75-2/A
Vicat Softening Temperature	98.0	°C	ISO 306/B50
CLTE - Flow	8.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Relative Permittivity			IEC 60250
100 Hz	3.00		
1 MHz	2.90		
Dissipation Factor			IEC 60250
100 Hz	6.0E-3		
1 MHz	9.0E-3		
Comparative Tracking Index	600	V	IEC 60112
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	220 to 260	°C	
Mold Temperature	70.0	°C	
Injection Velocity	240	mm/sec	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

