

Desmopan® DP 9380AU

Thermoplastic Polyurethane Elastomer (Polyether)

Covestro - PUR

Message:

Extrusion- and injection molding grade; very good hydrolysis and microbial resistance; good low-temperature flexibility; complies with VDE 0282-10; with special UV stabilizers; Application; Cable sheathings; Hoses, non-reinforced; Technical parts

General Information			
Features	Hydrolysis Resistant		
	Low Temperature Flexibility		
	Microbe Resistant		
Uses	Cable Jacketing		
	Engineering Parts		
	Hose		
Agency Ratings	VDE 0282-10		
RoHS Compliance	RoHS Compliant		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1110	kg/m ³	ISO 1183 ¹
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868 ²
Shore A, 3 sec	80		
Shore D, 15 sec	31		
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress ³			DIN 53504
Break, 23°C	40.9	MPa	
10% Strain, 23°C	1.40	MPa	
50% Strain, 23°C	3.80	MPa	
100% Strain, 23°C	5.10	MPa	
300% Strain, 23°C	8.90	MPa	
Tensile Strain ⁴ (Break, 23°C)	630	%	DIN 53504
Abrasion Resistance (23°C)	20.0	mm ³	ISO 4649-A
Tensile Storage Modulus			ISO 6721-1,-4
-20°C	73.0	MPa	
20°C	37.0	MPa	
60°C	30.0	MPa	

Impact Resilience (23°C)	50	%	ISO 4662
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ⁵ (23°C)	50	kN/m	ISO 34-1
Compression Set			ISO 815
23°C, 72 hr	25	%	
70°C, 24 hr	42	%	
Injection	Nominal Value	Unit	
Drying Temperature	< 80.0	°C	
Processing (Melt) Temp	205 to 225	°C	
Mold Temperature	20.0 to 40.0	°C	
Extrusion	Nominal Value	Unit	
Drying Temperature	< 80.0	°C	
Melt Temperature	195 to 215	°C	
NOTE			

1. Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

2. Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

3. 200 mm/min

4. 200 mm/min

5. 500 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

