

# ESENTTIA 08H85DB-BC

Polypropylene Homopolymer

Polipropileno del Caribe S.A.

Message:

Characteristics: Homopolymer polypropylene with excellent optical properties and processability, with high cleanness and clarity, with slip and antiblock additives.  
Recommended for: Non oriented TWQ films low gauge.

General Information			
Additive	Antiblock		
	Slip		
Features	Antiblocking		
	Clean/High Purity		
	Food Contact Acceptable		
	Good Processability		
	High Clarity		
	Homopolymer		
	Opticals		
	Slip		
Uses	Film		
Agency Ratings	EC 1907/2006 (REACH)		
	EC 1935/2004		
	EC 2023/2006		
	EU 10/2011		
	FDA 21 CFR 177.1520(a)(3)(i)(c)(1)		
	FDA 21 CFR 177.1520(b)		
	FDA 21 CFR 177.1520(c) 3.1a		
Forms	Pellets		
Processing Method	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) <sup>1</sup> (230°C/2.16 kg)	8.5	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>2</sup> (Yield, 3.20 mm, Injection Molded)	31.7	MPa	ASTM D638
Tensile Elongation <sup>3</sup> (Yield, 3.20 mm, Injection Molded)	11	%	ASTM D638
Flexural Modulus - 1% Secant <sup>4</sup> (3.20 mm, Injection Molded)	1240	MPa	ASTM D790A

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm, Injection Molded)	43	J/m	ASTM D256A
NOTE			
1.	Procedure B		
2.	Type I, 50 mm/min		
3.	Type I, 50 mm/min		
4.	Type I, 1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

