

# Lucent PBT GPB-130L

Polybutylene Terephthalate

Lucent Polymers, Inc.

## Message:

30% Glass Fiber Reinforced, Polybutylene Terephthalate

Recycled Content

Add "R" for Added Release

Add "U" for UV Stabilizer

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Recycled Content	Yes		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.50	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	117	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	6210	MPa	ASTM D790
Flexural Strength	159	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	152	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT