

Sarlink® TPV X6755 (PRELIMINARY DATA)

Thermoplastic Vulcanizate

Teknor Apex Company

Message:

SARLINK® TPV X6755 is a high performance thermoplastic vulcanizate used in automotive applications including interior trim. Sarlink TPV X6755 is a medium hardness, low density grade, available in Nat or can be color-matched with good color stability, exhibiting good UV resistance. This grade is designed for injection molding but could also be extruded.

General Information			
Features	Low Specific Gravity		
	Low compressive deformability		
	Low density		
	Light stabilization		
	Good UV resistance		
	Workability, good		
	Good formability		
	Good color stability		
	Good coloring		
	Good adhesion		
	Good chemical resistance		
	Medium hardness		
Uses	Seals		
	Application in Automobile Field		
	Car interior parts		
	Car interior equipment		
	Rubber substitution		
	Profile		
RoHS Compliance	RoHS compliance		
Appearance	Unspecified Color		
	Opacity		
	Available colors		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method

Durometer Hardness		ISO 868	
Shore A, 1 second, injection molding	60	ISO 868	
Shore A, 5 seconds, injection molding	58	ISO 868	
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	1.90	MPa	ISO 37
Tensile Stress (Break)	5.35	MPa	ISO 37
Tensile Elongation (Break)	630	%	ISO 37
Compression Set (70°C, 22 hr)	38	%	ISO 815
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (200°C, 206 sec ⁻¹)	216	Pa · s	ASTM D3835
Legal statement			

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Injection	Nominal Value	Unit
Drying Temperature	82	°C
Drying Time	3.0	hr
Rear Temperature	177 - 216	°C
Middle Temperature	177 - 216	°C
Front Temperature	177 - 216	°C
Nozzle Temperature	188 - 221	°C
Processing (Melt) Temp	182 - 221	°C
Mold Temperature	10 - 66	°C
Back Pressure	0.0689 - 1.03	MPa
Screw Speed	100 - 200	rpm
Screw L/D Ratio	20.0:1.0	
Extrusion	Nominal Value	Unit
Drying Temperature	82	°C
Drying Time	3.0	hr
Cylinder Zone 1 Temp.	182 - 204	°C
Cylinder Zone 2 Temp.	182 - 204	°C
Cylinder Zone 3 Temp.	188 - 210	°C
Cylinder Zone 4 Temp.	188 - 210	°C
Melt Temperature	193 - 216	°C
Die Temperature	193 - 216	°C
Take-Off Roll	21 - 49	°C
Extrusion instructions		

Screen Pack: 20 to 60 meshScrew: 3:1 Compression Ratio

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

