NEMCON E ABS 20CF

High Density Polyethylene

Ovation Polymers Inc.

Message:

Nemcon^T E-series products are designed for use in ESDA electronic assembly environments where strict control of ESD and cleanliness are critical. Nemcon^T E ABS 20CF is a high modulus carbon fiber-reinforced ABS with excellent conductivity. It is suitable for a wide variety of injection molding applications, including electronic components, shipping trays, storage racks, electronic housings and work surfaces.

General Information			
Filler / Reinforcement	Carbon Fiber		
Features	Clean/High Purity		
	Conductive		
	ESD Protection		
Uses	Electrical Housing		
	Electrical Parts		
	Electrical/Electronic Applications		
	Support Trays		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹ (23°C)	10500	MPa	ASTM D638
Tensile Strength ² (Break, 23°C)	95.0	MPa	ASTM D638
Tensile Elongation ³ (Break, 23°C)	1.9	%	ASTM D638
Flexural Modulus ⁴ (23°C)	9540	MPa	ASTM D790
Flexural Strength ⁵ (Yield, 23°C)	128	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	46	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8			
MPa, Unannealed, 3.20 mm)	98.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	2.8E+3	ohms	ASTM D257
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	1.3 mm/min		

5. 1.3 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

