

SWANCOR Epoxy 976

Epoxy; Epoxide

SWANCOR IND. CO., LTD.

Message:

Modified Bisphenol A epoxy vinyl ester resin.

Good heat distortion temperature and improved toughness.

Excellent fatigue resistance.

Suitable for compression molding process

General Information			
Filler / Reinforcement	Styrene,42% Filler by Weight		
Features	Fatigue Resistant		
	Good Toughness		
	High Heat Resistance		
Forms	Liquid		
Processing Method	Compression Molding		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	115	°C	ASTM D648
Thermoset	Nominal Value	Unit	Test Method
Shelf Life (25°C)	17	wk	
Thermoset Mix Viscosity (25°C)	2600	cP	ASTM D2393

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT