# **ADDINYL A2 ZG30**

### Polyamide 66

#### **ADDIPLAST**

#### Message:

ADDINYL A2 ZG30 is a Polyamide 66 (Nylon 66) material filled with 30% glass bead. It is available in Africa & Middle East, Asia Pacific, Europe, or Latin

Important attributes of ADDINYL A2 ZG30 are:

Good Dimensional Stability

**Heat Resistant** 

Rigid

Typical applications include:

Appliances

Electrical/Electronic Applications

Engineering/Industrial Parts

General Information							
Filler / Reinforcement		Glass Bead,30% Filler by Weight					
Features		Good Dimensional Stability					
		Good Heat Aging Resistance					
		High Rigidity					
Uses		Appliance Components					
		Electrical/Electronic Applications					
		Gears	Gears				
Forms		Pellets	Pellets				
Physical	Dry	Conditioned	Unit	Test Method			
Density	1.35	<del></del>	g/cm³	ISO 1183/A			
Hardness	Dry	Conditioned	Unit	Test Method			
Shore Hardness (Shore D)	87	82		ISO 868			
Mechanical	Dry	Conditioned	Unit	Test Method			
Tensile Stress (Break)	80.0	60.0	MPa	ISO 527-2			
Tensile Strain (Break)	7.0	11	%	ISO 527-2			
Flexural Modulus	3800	1800	МРа	ISO 178			
Impact	Dry	Conditioned	Unit	Test Method			
Charpy Notched Impact Strength	3.0	5.0	kJ/m²	ISO 179/1eA			
Charpy Unnotched Impact Strength	40	60	kJ/m²	ISO 179/1eU			
Notched Izod Impact Strength	3.5	7.0	kJ/m²	ISO 180/1A			
Thermal	Dry	Conditioned	Unit	Test Method			
Heat Deflection Temperature (1.8 MPa,							
Unannealed)	95.0		°C	ISO 75-2/Af			

Melting Temperature (DSC)	260		°C	ISO 3146
CLTE - Flow	6.0E-5		cm/cm/°C	ASTM E831
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity	1.0E+15	1.0E+13	ohms·cm	IEC 60093
Electric Strength	30	25	kV/mm	IEC 60243-1
Comparative Tracking				
Index (Solution A)	450		V	IEC 60112

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

