Braskem PP DR152.00

Polypropylene Random Copolymer

Braskem Europe GmbH

Message:

DR152.00 is developmental performance random copolymer for blow moulding applications. This polypropylene resin exhibits efficient processing, good transparency and contact clarity at balanced level of mechanical properties.

Applications:

Blow molded containers

Thermoformed containers

Process:

Blow Moulding and Sheet extrusion

General Information			
Features	Good Clarity		
	Workability, good		
	Random copolymer		
Uses	Blown Containers		
	Blow molding applications		
	Sheet		
	Thermoformed container		
	Container		
Agency Ratings	FDA FCN 909		
	Europe 10/1/2011 12:00:00 AM		
Processing Method	Blow molding		
	Sheet extrusion molding		
	Thermoforming		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	2.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus (Injection Molded)	1100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C,		2	
Injection Molded)	8.5	kJ/m²	ISO 179/1eA

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

