

Petrothene® LP500210

High Density Polyethylene

LyondellBasell Industries

Message:

The PETROTHENE LP5002 series of polyethylene resins exhibits excellent environmental stress crack resistance and is especially designed for bottles containing aggressive agricultural and household chemicals.

General Information			
Additive	Antistatic		
Features	Antistatic		
	Food Contact Acceptable		
	High ESCR (Stress Crack Resist.)		
Uses	Bottles		
	Profiles		
	Sheet		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Blow Molding		
	Profile Extrusion		
	Sheet Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.946	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.20	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance			
F50	> 1000	hr	ASTM D2561
50°C, 10% Igepal CO-630, F50	> 1000	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	65		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	23.4	MPa	ASTM D638
Tensile Elongation (Break)	> 800	%	ASTM D638
Flexural Modulus	965	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Tensile Impact	131	J/cm	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	66.0	°C	ASTM D648

Brittleness Temperature	< -76.0	°C	ASTM D746
Vicat Softening Temperature	122	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

