

MACOMASS PVC MM-PVC I 1560

Flexible Polyvinyl Chloride

MACOMASS Verkaufs AG

Message:

PVC plasticized compound, injection

General Information			
Additive	Plasticizer		
Features	Low (to no) lead content		
	Non-DEHP plasticizer		
	Calcium content, low (to none)		
Appearance	Light Blue		
	Clear/transparent		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.14 - 1.18	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 3 sec)	56 - 62		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	> 8.00	MPa	ISO 527-2
Tensile Strain (Break)	> 300	%	ISO 527-2
Injection	Nominal Value	Unit	
Processing (Melt) Temp	170	°C	
Mold Temperature	30	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT