

VENYL UFRW309 - 8229

Polyamide 66

AD majoris

Message:

VENYL UFRW309 - 8229 is a halogen free flame retardant compounds UL 94 V0 with 30% glass beads reinforced polyamide 66 intended for Injection moulding.

APPLICATIONS

VENYL UFRW309 - 8229 has been developed especially for very demanding applications in automotive industry and electrical parts.

Products requiring excellent combination between thermal and mechanical properties, good surface quality, good compression strength.

VENYL UFRW309 - 8229 is available in black and limited colours.

General Information			
Filler / Reinforcement	Glass Bead,30% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Compressive Strength		
	Good Surface Finish		
	Halogen Free		
	Recyclable Material		
Uses	Automotive Applications		
	Electrical Parts		
Appearance	Black		
	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ISO 1183
Molding Shrinkage	0.80 to 1.2	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	0.60	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	95.0	MPa	ISO 527-2
Tensile Strain (Break)	9.0	%	ISO 527-2
Flexural Modulus	4900	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	4.0	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	240	°C	ISO 75-2/B

1.8 MPa, Unannealed	210	°C	ISO 75-2/A
Melting Temperature (DSC)	256	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	475	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-0		UL 94
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Rear Temperature	270 to 285	°C	
Middle Temperature	265 to 280	°C	
Front Temperature	260 to 285	°C	
Nozzle Temperature	265 to 280	°C	
Mold Temperature	80.0 to 100	°C	
Injection Pressure	85.0 to 110	MPa	
Injection Rate	Fast		
Holding Pressure	50.0 to 70.0	MPa	
Screw L/D Ratio	15.0:1.0 to 20.0:1.0		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT