Spartech Polycom SC1-5090

Acrylonitrile Butadiene Styrene

Spartech Polycom

Message:

Spartech SC1-5090 is a medium viscosity ABS resin for injection molding. It is heat stabilized and lubricated for good processing characteristics, and it exhibits good impact and chemical resistance.

With the benefit of low moisture absorption, ABS can be used in a variety of environments. Being a very versatile product, SC1-5090 can be used for industrial, transportation, sporting goods and electrical/electronic applications.

| General Information | | | | | |
|---------------------------|------------------------------------|----------|-------------|--|--|
| Additive | heat stabilizer Lubricant | | | | |
| | | | | | |
| | | | | | |
| Features | Low hygroscopicity | | | | |
| | Impact resistance, good | | | | |
| | Workability, good | | | | |
| | Good chemical resistance | | | | |
| | Thermal Stability | | | | |
| | Thermal stability, good | | | | |
| | Lubrication | | | | |
| | General | | | | |
| | Medium viscosity | | | | |
| | | | | | |
| Uses | Electrical/Electronic Applications | | | | |
| | Industrial application | | | | |
| | Application in Automobile Field | | | | |
| | Sporting goods | | | | |
| | General | | | | |
| | | | | | |
| Appearance | Available colors | | | | |
| | Natural color | | | | |
| | | | | | |
| Forms | Particle | | | | |
| Processing Method | Injection molding | | | | |
| Physical | Nominal Value | Unit | Test Method | | |
| Specific Gravity | 1.04 | g/cm³ | ASTM D792 | | |
| Melt Mass-Flow Rate (MFR) | 5.0 | g/10 min | ASTM D1238 | | |
| Mechanical | Nominal Value | Unit | Test Method | | |
| Tensile Strength (23°C) | 41.4 | МРа | ASTM D638 | | |
| Flexural Modulus (23°C) | 2280 | МРа | ASTM D790 | | |
| Impact | Nominal Value | Unit | Test Method | | |

| Notched Izod Impact (23°C) | 270 | J/m | ASTM D256 |
|-------------------------------------|---------------|------|-------------|
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (| 0.45 | | |
| MPa, Unannealed) | 94.0 | °C | ASTM D648 |
| Injection | Nominal Value | Unit | |
| Drying Temperature | 87.8 | °C | |
| Drying Time | 2.0 - 4.0 | hr | |
| Rear Temperature | 210 - 240 | °C | |
| Middle Temperature | 215 - 245 | °C | |
| Front Temperature | 220 - 250 | °C | |
| Nozzle Temperature | 218 - 260 | °C | |
| Processing (Melt) Temp | 218 - 260 | °C | |
| Mold Temperature | 43.3 - 65.6 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

