## KumhoSunny PC/PET KCA9360

Polycarbonate + PET

Shanghai KumhoSunny Plastics Co., Ltd.

## Message:

KCA9360 is PC/PET resin. KCA9360 has ability to resist 750°C, high heat resistance, high tenacity and high chem-resistance. KCA9360 is mainly used in switch panel, control temp. panel, electron & electric parts etc.

General Information			
Features	Good Chemical Resistance		
	High Heat Resistance		
Uses	Electrical Parts		
	Electrical/Electronic Application	ns	
UL File Number	E254819		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	35	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	53.0	MPa	ASTM D638
Flexural Modulus	2000	MPa	ASTM D790
Flexural Strength	68.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	700	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	125	°C	ASTM D1525 <sup>1</sup>
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Glow Wire Flammability Index	750	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	100 to 110	°C	
Drying Time	4.0 to 6.0	hr	
Processing (Melt) Temp	230 to 260	°C	
Mold Temperature	50.0 to 90.0	°C	

Rate B (120°C/h)

1.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

