

KOCETAL® WR701LOBE

Acetal (POM) Copolymer
Kolon Plastics, Inc.

Message:

KOCETAL® WR701LOBE is an Acetal (POM) Copolymer product. It is available in Asia Pacific, Europe, Latin America, or North America. Typical application: Automotive.
Characteristics include:
Flame Rated
Good UV Resistance
Low to No Odor/Taste
UV Stabilized

General Information			
Additive	UV Stabilizer		
Features	Good UV Resistance		
	Low to No Odor		
Uses	Automotive Applications		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	25	g/10 min	ASTM D1238
Molding Shrinkage - Flow	2.0	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 60% RH)	0.22	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	80		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	59.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	66	%	ASTM D638
Flexural Modulus (23°C)	2600	MPa	ASTM D790
Flexural Strength (23°C)	91.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648A
0.45 MPa, Unannealed	158	°C	
1.8 MPa, Unannealed	105	°C	
Vicat Softening Temperature	162	°C	ASTM D1525
Melting Temperature	166	°C	ASTM D1525
CLTE - Flow	1.3E-4	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	ASTM D257

Volume Resistivity	1.0E+11	ohms·cm	ASTM D257
Dielectric Strength	19	kV/mm	ASTM D149
Dielectric Constant	3.70		ASTM D150
Dissipation Factor (1 MHz)	6.0E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Additional Information	Nominal Value	Unit	Test Method
Formaldehyde Level	1	ppm	VDA 275

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT