# SUPRAN® PP1350

### Polypropylene

#### SAMBARK

#### Message:

SUPRAN® is injection-moldable Long Fiber Reinforced Thermoplastics(LFT), PP1350 is Polypropylene reinforced with 50wt% long glass fibers. Parts molded of SUPRAN® have outstanding mechanical properties such as high strength, stiffness, impact and creep resistance and low warpage combined with high heat deflection. SUPRAN® PP1350 is suitable for structural parts in automotive and industrial application.

General Information			
UL YellowCard	E230962-230053		
Filler / Reinforcement	Long Glass Fiber,50% Filler by Weight		
Features	Good Creep Resistance		
	High Impact Resistance		
	High Stiffness		
	High Strength		
	Low Warpage		
Uses	Automotive Applications		
	Housings		
	Industrial Applications		
	Pump Parts		
	Structural Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.20	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	142	MPa	ASTM D638
Tensile Elongation (Break)	2.7	%	ASTM D638
Flexural Modulus	9810	MPa	ASTM D790
Flexural Strength	186	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C	300	J/m	
23°C	290	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	165	°C	ASTM D648

Injection	Nominal Value	Unit
Rear Temperature	215 to 230	°C
Middle Temperature	215 to 230	°C
Front Temperature	215 to 230	°C
Mold Temperature	40.0 to 70.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

