

Lucon® PN9008

Polyphenylene Sulfide

LG Chem Ltd.

Message:

Lucon®PN9008 is a polyphenylene sulfide (PPS) material, which contains a filler of glass/mineral. This product is available in North America, Latin America, Europe or Asia Pacific. The processing method is injection molding.

Lucon®The main features of PN9008 are:

flame retardant/rated flame

Conductivity

chemical resistance

Heat resistance

Typical application areas include:

Electrical/electronic applications

House

General Information			
UL YellowCard	E248280-100040860	E67171-339434	
Filler / Reinforcement	Glass \Mineral		
Features	Heat conduction		
	Good chemical resistance		
	Heat resistance, high		
Uses	Electric Motor Housings		
	Electrical/Electronic Applications		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.94	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.40 - 1.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	73.5	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	< 5.0	%	ASTM D638
Flexural Modulus ³ (6.40 mm)	12900	MPa	ASTM D790
Flexural Strength ⁴ (6.40 mm)	127	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	20	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 6.40 mm)	250	°C	ASTM D648
Peak Melting Temperature	280	°C	ASTM D3418
Thermal Conductivity ⁵	1.7	W/m/K	
Electrical	Nominal Value	Unit	Test Method

Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+18	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	V-0		UL 94
1.60 mm	V-0		UL 94
2.50 mm	V-0		UL 94
3.20 mm	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120 - 140	°C	
Drying Time	3.0 - 5.0	hr	
Rear Temperature	280 - 310	°C	
Middle Temperature	310 - 320	°C	
Front Temperature	320 - 325	°C	
Nozzle Temperature	310 - 330	°C	
Processing (Melt) Temp	330	°C	
Mold Temperature	130 - 150	°C	
Back Pressure	0.981 - 3.92	MPa	
Screw Speed	40 - 80	rpm	
Injection instructions			
Minimum Moisture Content: 0.01%			
NOTE			
1.	5.0 mm/min		
2.	5.0 mm/min		
3.	1.0 mm/min		
4.	1.0 mm/min		
5.	Laser flash Method		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT