

# NEXT REPROCESSED PA6 8267-300R

Polyamide 6

NEXT Specialty Resins, Inc.

## Message:

NEXT REPROCESSED PA6 8267-300R is a Polyamide 6 (Nylon 6) material filled with 40% glass fiber. It is available in North America.

Important attributes of NEXT REPROCESSED PA6 8267-300R are:

Eco-Friendly/Green

Good Dimensional Stability

Heat Resistant

Typical application of NEXT REPROCESSED PA6 8267-300R: Automotive

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Recycled Content	Yes		
Features	Good Dimensional Stability		
	High Heat Resistance		
Uses	Automotive Applications		
Appearance	Black		
Forms	Pellets, Reprocessed		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.48	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	37 to 43	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	190	MPa	ASTM D790
Tensile Strength	103	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	190	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	199	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

