

Latimass 75/4-04 D009

Polybutylene Terephthalate

LATI S.p.A.

Message:

Specific density compound based on Polybutylene Terephthalate (PBT).

General Information			
Physical	Nominal Value	Unit	Test Method
Density	1.00	g/cm³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.90 to 1.2	%	
Flow : 2.00 mm	1.0 to 1.3	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3400	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	25.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	0.70	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	1.2	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	10	kJ/m²	ISO 179/1eU
Notched Izod Impact (23°C)	10	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	165	°C	ISO 75-2/B
1.8 MPa, Unannealed	70.0	°C	ISO 75-2/A
Vicat Softening Temperature	180	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature	120 to 130	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	230 to 250	°C	
Mold Temperature	70.0 to 90.0	°C	
Injection Rate	Moderate		

NOTE

1. at 60 MPa of cavity pressure

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

