

Ravalene CR C 7644

Linear Low Density Polyethylene

Ravago Group

Message:

IQ compound LLDPE black for rotomoulding

General Information			
Recycled Content	Yes		
Appearance	Black		
Processing Method	Rotational Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.935	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	15.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	22	%	
Break	350	%	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

