

Stylac™ R440T

Acrylonitrile Styrene Copolymer
Asahi Kasei Chemicals Corporation

Message:

Stylac™ R440T is an Acrylonitrile Styrene Copolymer (AS) product filled with glass fiber. It is available in Africa & Middle East, Asia Pacific, or Europe.
Typical application: Industrial Applications.
Characteristics include:
Flame Rated
High Strength

General Information			
UL YellowCard	E171626-225698		
Filler / Reinforcement	Glass Fiber		
Features	High Strength		
Uses	Industrial Applications		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.22	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	11	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	10.0	cm³/10min	ISO 1133
Molding Shrinkage - Flow	0.15 to 0.35	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	114	MPa	ISO 527-2/5
Flexural Modulus ¹	7950	MPa	ISO 178
Flexural Stress ²	170	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	109	°C	ISO 75-2/A
CLTE - Flow	2.8E-5	cm/cm/°C	ASTM D696
RTI Elec	50.0	°C	UL 746
RTI Imp	50.0	°C	UL 746
RTI Str	50.0	°C	UL 746
Ball Pressure Test ³	100	°C	EMAC
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		
3.	Registered Number: B-1574		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

