

# Tenite™ Butyrate 530E3720005 Clear, Trsp

Cellulose Acetate Butyrate  
Eastman Chemical Company

## Message:

Tenite™ cellulosic plastics are noted for their excellent balance of properties - toughness, hardness, strength, surface gloss, clarity, and a warm feel. The mechanical properties of Tenite™ cellulosic plastics differ with plasticizer levels. Lower plasticizer content yields a harder surface, higher heat resistance, greater rigidity, higher tensile strength, and better dimensional stability. Higher plasticizer content increases impact strength. Tenite™ cellulosic plastics are available in natural, clear, selected ambers, or smoke transparents and black translucent. Color concentrates are available in let-down ratios from 10:1 to 40:1. Tenite™ Cellulose Acetate Butyrate 530-05 contains an odor mask and has a plasticizer level of 5%.

General Information	
Additive	Plasticizer (5%)
Features	Good Strength
	Good Toughness
	High Clarity
	High Gloss
	High Hardness
	Low to No Odor
	Plasticized
	Renewable Resource Content
Uses	Soft
	Coating Applications
	Amber
	Black
	Clear/Transparent
Appearance	Natural Color
Forms	Pellets

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT