# polyvic® M-1828-GL

### Polyvinyl Chloride

## Unipack Plasindo

#### Message:

PVC Compound Low Impact Strength

M-1828-GL, High clarity with total clear, has an balance stiffness and impact resist, designed for bottle application under 300 ml (Depend design and wall thickness of the bottle)

Features

Low Impact Strength

**High Clarity** 

Processing Methode

**Blow Molding** 

**Typical Applications** 

Bottle

General Information				
Features	Good Impact Resistance			
	Good Stiffness			
	High Clarity			
Uses	Bottles			
Appearance	Clear/Transparent			
Processing Method	Blow Molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.36	g/cm³	ASTM D792	
Hardness	Nominal Value	Unit	Test Method	
Rockwell Hardness (R-Scale)	17		ASTM D785	
Durometer Hardness (Shore A)	81		ASTM D2240	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength	58.8	МРа	ASTM D638	
Tensile Elongation (Break)	180	%	ASTM D638	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact	76	J/m	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load (1.8 MPa, Unannealed)	55.2	°C	ASTM D648	
Vicat Softening Temperature	81.6	°C	ASTM D256	
Flammability	Nominal Value	Unit	Test Method	
Burning Rate	3.4	mm/min	ASTM D635	
Optical	Nominal Value	Unit	Test Method	
Transmittance	90.0	%	ASTM D1003	
Extrusion	Nominal Value	Unit		
Hopper Temperature	160 to 170	°C		

Cylinder Zone 1 Temp.	160 to 170	°C	
Cylinder Zone 2 Temp.	170 to 180	°C	
Cylinder Zone 3 Temp.	180 to 185	°C	
Cylinder Zone 4 Temp.	185 to 190	°C	
Cylinder Zone 5 Temp.	185 to 190	°C	
Die Temperature	185 to 195	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

