

DESLOY™ DSC891B

Polycarbonate + ABS

DESCO Co., Ltd.

Message:

Descriptions: DESLOY™ DSC891B is PC & ABS alloy resin which has an advantage of both resins. It has good rigidity and toughness. DESLOY™ DSC891B also has low water absorption and excellent dimensional stability.

Applications: DESLOY™ DSC891B is suitable for automotive parts, in example electronic cover which request good mechanical property and low deformation property.

General Information			
Features	Good dimensional stability		
	Rigidity, high		
	Good toughness		
	Low or no water absorption		
Uses	Automotive Electronics		
	Application in Automobile Field		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 - 0.70	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	53.9	MPa	ASTM D638
Tensile Elongation (Break)	80	%	ASTM D638
Flexural Modulus	2450	MPa	ASTM D790
Flexural Strength	83.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	690	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	105	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	100 - 120	°C	
Drying Time	3.0 - 5.0	hr	
Suggested Max Moisture	< 0.20	%	
Rear Temperature	250 - 260	°C	

Middle Temperature	260 - 270	°C
Front Temperature	260 - 280	°C
Nozzle Temperature	260 - 280	°C
Processing (Melt) Temp	260 - 280	°C
Mold Temperature	60.0 - 90.0	°C

Injection instructions

Speed: 40 to 70%Pressure 1st: 30 to 60%Pressure 2nd: 30 to 60Holding Pressure: 10 to 20%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

