

ENVIROSUN® ENV32-NC090

Acrylonitrile Styrene Acrylate + PC

ENVIROPLAS®, Inc.

Message:

Injection Molding Grade, Good Weather Resistance, High Heat Resistance, High Impact Resistance, RoHS Compliant

NC090 = To Be Assigned 5 Digit Number Indicating Natural, Black, or Custom Color.

The ENVIROSUN™ Series Products Are Available With Mold Release and/or UV Stabilizer.

Contact Enviroplas Regarding UL Recognized Versions Of This Product.

General Information			
Features	Good Weather Resistance		
	High Heat Resistance		
	High Impact Resistance		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (280°C/3.8 kg)	22	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	60.0	MPa	ASTM D638
Tensile Elongation (Break)	25	%	ASTM D638
Flexural Modulus	2390	MPa	ASTM D790
Flexural Strength	82.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	290	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	103	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	98.9	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	227 to 249	°C	
Middle Temperature	238 to 249	°C	
Front Temperature	249 to 271	°C	

Nozzle Temperature	260 to 282	°C
Mold Temperature	54.4 to 73.9	°C
Injection Rate	Moderate	
Back Pressure	0.345 to 1.03	MPa
Screw Speed	30 to 70	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT