

Kepamid® 2300SU

Polyamide 66

Korea Engineering Plastics Co., Ltd

Message:

Kepamid® 2300SU is a Polyamide 66 (Nylon 66) material. It is available in Asia Pacific, Europe, or North America.

Important attributes of Kepamid® 2300SU are:

Flame Rated

Impact Resistant

Warp Resistant

Typical applications include:

Automotive

Electrical/Electronic Applications

General Information			
Features	Good Impact Resistance		
	Low Warpage		
Uses	Automotive Applications		
	Electrical/Electronic Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.09	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (275°C/2.16 kg)	3.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	117		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	56.9	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	50	%	ASTM D638
Flexural Modulus (23°C)	2160	MPa	ASTM D790
Flexural Strength (Yield, 23°C)	81.4	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	390	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	260	°C	DSC
Flammability	Nominal Value		Test Method
Flame Rating (0.800 mm)	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

