

MAJORIS BG200E

High Density Polyethylene

AD majoris

Message:

BG200E is a 20% glass fibre reinforced polyethylene high density compound intended for injection moulding and extrusion profiles.

The product is available in black (BG200E - 8229) and natural (BG200E) but other colours can be provided on request.

APPLICATIONS

BG200E is intended for components which require good impact strength, rigidity, dimensional stability.

Suitable applications are:

Electrical tool and appliance components

Miscellaneous automotive technical items

Profile

General Information	
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight
Features	Good dimensional stability
	Rigidity, high
	High density
	Impact resistance, good
	Recyclable materials
Uses	Electrical/Electronic Applications
	Power/other tools
	Home appliance components
	Application in Automobile Field
	Profile
Appearance	Black
	Available colors
	Natural color
Forms	Particle
Processing Method	Profile extrusion molding
	Injection molding

Physical	Nominal Value	Unit	Test Method
Density	1.09	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)	2.0 - 4.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	39.0	MPa	ISO 527-2/50
Tensile Strain (Break)	7.0	%	ISO 527-2/50
Flexural Modulus	2900	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	12	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	120	°C	ISO 75-2/B
1.8 MPa, not annealed	100	°C	ISO 75-2/A
Injection	Nominal Value	Unit	
Rear Temperature	180 - 200	°C	
Processing (Melt) Temp	190 - 230	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Rate	Moderate		
Injection instructions			

Holding pressure: 50 to 70% of the injection pressure

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

