

POLYCOMPO PE 3300F

High Density Polyethylene

POLYCOMPO Co.,Ltd.

Message:

POLYCOMPO PE 3300F is a High Density Polyethylene product. It can be processed by blown film and is available in Asia Pacific. Applications of POLYCOMPO PE 3300F include film and packaging.

General Information			
Uses	Film		
	Packaging		
Forms	Pellets		
Processing Method	Blown Film		
Physical	Nominal Value	Unit	Test Method
Density	0.950	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)	1.1	g/10 min	ISO 1133
Environmental Stress-Cracking Resistance (Injection Molded)	30.0	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, Injection Molded)	62		ASTM D2240, ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
Yield, Injection Molded	21.0	MPa	
Break, Injection Molded	30.0	MPa	
Tensile Strain (Break, Injection Molded)	500	%	ISO 527-2
Flexural Modulus (Injection Molded)	780	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-60.0	°C	ASTM D746A, ISO 974
Vicat Softening Temperature	123	°C	ASTM D1525, ISO 306
Peak Crystallization Temperature (DSC)	132	°C	ASTM D3418, ISO 3146

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

