Gallonprene® GP100-6002

Thermoplastic Elastomer

Shenzhen Sungallon Rubber & Plastic Corporation Limited

Message:

Halogen-free

Gallonprene® GP100-6002 is a thermoplastic elastomer (TPE) product. It can be processed by injection molding and is available in Africa and the Middle East, Latin America or Asia Pacific. Gallonprene® GP100-6002 application areas include engineering/industrial accessories, consumer goods and handles. Features include:

Comply with REACH standard ROHS certification high gloss

General Information			
Features	Highlight		
	Sprayable		
	Halogen-free		
Uses	overmolding		
	Soft handle		
	Toys		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Appearance	Clear/transparent		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.938	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/1.0 kg)	23	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 23°C)	60		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	4.50	MPa	ASTM D412
Tensile Elongation ² (Break)	700	%	ASTM D412
Injection	Nominal Value	Unit	
Rear Temperature	130 - 150	°C	
Middle Temperature	140 - 160	°C	
Front Temperature	150 - 170	°C	
Processing (Melt) Temp	110 - 130	°C	
Mold Temperature	30.0 - 60.0	°C	
Injection Rate	Slow		
Injection instructions			

Processing Temperature Limit: 220°CInjection Pressure: LowBack Pressure: 20 to 50%Overmolding Parameters:Rear Temperature: 150 to 170°CCenter Temperature: 160 to 180°CFront Temperature: 170 to 190°CMelt Temperature: 110 to 130°CMold Temperature: 30 to 60°CProcessing Temperature Limit: 220°CInjection Pressure: LowInjection Speed: LowBack Pressure: 20 to 50%

NOTE		
1.	500 mm/min	
2.	500 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

