Microthene® F FA70000

High Density Polyethylene LyondellBasell Industries

Message:

Microthene F polyolefin powders are ultra-fine, spherically shaped particles with narrow size distribution suitable for use in a broad range of specialty applications. Microthene F powders combine the unique properties of a polyolefin resin with a microfine particle size.

| General Information | | | |
|-------------------------------------|---------------------|----------|-------------|
| Agency Ratings | FDA 21 CFR 177.1520 | | |
| Forms | Powder | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.952 | g/cm³ | ASTM D1505 |
| Melt Mass-Flow Rate (MFR) (190°C/2. | 16 | | |
| kg) | 10 | g/10 min | ASTM D1238 |
| Average Particle Size | 20 | μm | ETM Malvern |
| Particle Shape | Spherical | | |
| Particle Size Distribution | 5.0 to 50.0 | μm | ETM Malvern |
| Maximum Moisture Content | 0.10 | % | ETM 156 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore D) | 66 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Break) | 11.7 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 400 | % | ASTM D638 |
| Flexural Modulus | 1100 | MPa | ASTM D790 |
| Thermal | Nominal Value | Unit | Test Method |
| Brittleness Temperature | -76.0 | °C | ASTM D746 |
| Vicat Softening Temperature | 125 | °C | ASTM D1525 |
| Peak Melting Temperature | 134 | °C | ASTM D3418 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

