

Menzolit® SMC 0150

Thermoset Polyester

Menzolit Ltd (UK)

Message:

Menzolit® SMC 0150 is a sheet moulding compound based on unsaturated polyester resin. The product is glass fibre reinforced and contains mineral fillers. In case of fire the product doesn't melt, neither does it form droplets nor is smoke generation excessive. The material is compression moulded in heated steel moulds. It is recommended to work with chrome plated tools. The product contains no halogens.

Menzolit® SMC 0150 is a general purpose SMC for applications in the field of electrical industry. Typical applications are housings, covers, wire distribution boxes and metering cabinets. The material meets the demands of DIN 16913 and is classified as type 830 (830.5) regarding mechanical properties. The flammability meets the demands of standard UL 94 category HB. The glass content is on a level that combines good mouldability with good mechanical properties regarding strength and stiffness.

General Information			
Filler / Reinforcement	Glass\Mineral,25% Filler by Weight		
Features	Flame Retardant		
	General Purpose		
	Good Moldability		
	Good Stiffness		
	Good Strength		
	Halogen Free		
	High Heat Resistance		
	Low Smoke Emission		
Uses	Electrical/Electronic Applications		
	General Purpose		
	Housings		
Agency Ratings	DIN 16913 type 830.5		
Appearance	Colors Available		
Forms	SMC - Sheet Molding Compound		
Processing Method	Compression Molding		
Part Marking Code (ISO 11469)	>UP-(MD+GF)70<		
Physical	Nominal Value	Unit	Test Method
Density	1.80	g/cm ³	ISO 1183
Molding Shrinkage			
-- ¹	0.0	%	DIN 53464
--	0.070	%	ISO 2577
Water Absorption (Saturation, 23°C)	< 0.50	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (Compression Molded)	12000	MPa	ISO 527-2
Tensile Stress (Yield, Compression Molded)	62.0	MPa	ISO 527-2
Flexural Modulus (Compression Molded)	10000	MPa	ISO 178

Flexural Stress (Compression Molded)	150	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (Compression Molded)	68	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	> 200	°C	ISO 75-2/A
Continuous Use Temperature	165	°C	Internal Method
Glass Transition Temperature	170	°C	DSC
CLTE - Flow	1.2E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.00 mm)	HB		UL 94
Glow Wire Ignition Temperature	750	°C	IEC 60695-2-13
Oxygen Index	22	%	ISO 4589-2
Additional Information	Nominal Value		Test Method
Glow Bar	Level BH 2 <= 95		IEC 60707-3
Injection	Nominal Value	Unit	
Mold Temperature	135 to 150	°C	
Injection Pressure	8.00 to 10.0	MPa	
NOTE			
1.	Post Molding Shrinkage		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT