

SHIN-A SEW-700X70

Epoxy; Epoxide

SHIN-A T&C;

Message:

Low Yellowing Epoxy

General Information	
---------------------	--

Uses	Coating Applications
	Paint

Physical	Nominal Value	Unit
Color	< 1.0	G
Viscosity (25°C)	7.00 to 14.0	Pa·s
Epoxy Equivalent	650 to 750	g/eq

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material
--


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT