

Bergamid™ B70 G50 H Black

Polyamide 6
PolyOne Corporation

Message:
Bergamid B70 G50 H Black is a Polyamide 6 (Nylon 6) product filled with 50% glass fiber. It can be processed by injection molding and it is heat stabilized.

General Information			
Filler / Reinforcement	Glass Fiber,50% Filler by Weight		
Features	Heat Stabilized		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.55	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	15000	MPa	ISO 527-2
Tensile Strength	220	MPa	ISO 527
Tensile Strain (Break)	2.0	%	ISO 527
Flexural Strength	320	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	15	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	85	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	210	°C	ISO 75-2/A
Continuous Use Temperature	120	°C	IEC 216
Melting Temperature (DSC)	215 to 225	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+16	ohms · cm	IEC 60093
Electric Strength	90	kV/mm	IEC 60243-1
Relative Permittivity	4.20		IEC 60250
Dissipation Factor	0.014		IEC 60250
Comparative Tracking Index	500	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	

Processing (Melt) Temp	250 to 280	°C
Mold Temperature	50.0 to 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

