

LEXAN™ FST9705 resin

Polycarbonate

SABIC Innovative Plastics

Message:

High viscosity PC Copolymer, OSU 55/55 compliant, low smoke, flame retardant resin

General Information			
Additive	Flame retardancy		
Features	Low smoke		
	Copolymer		
	Viscosity, High		
	Flame retardancy		
Agency Ratings	OSU 55/55		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	5.0	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR)			ISO 1133
300°C/1.2 kg	4.00	cm ³ /10min	ISO 1133
300°C/5.0 kg	16.8	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.60 - 0.80	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.28	%	ISO 62
Equilibrium, 23°C, 50% RH	0.11	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2620	MPa	ASTM D638
--	2500	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	72.3	MPa	ASTM D638
Yield	74.0	MPa	ISO 527-2/50
Fracture ³	73.2	MPa	ASTM D638
Fracture	76.6	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	6.7	%	ASTM D638
Yield	6.8	%	ISO 527-2/50
Fracture ⁵	100	%	ASTM D638
Fracture	110	%	ISO 527-2/50
Flexural Modulus			

50.0mm span ⁶	2500	MPa	ASTM D790
-- ⁷	2330	MPa	ISO 178
Flexural Stress			
--	107	MPa	ISO 178
Yield, 50.0mm span ⁸	115	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	24	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	110	J/m	ASTM D256
23°C	190	J/m	ASTM D256
-30°C ¹⁰	10	kJ/m ²	ISO 180/1A
23°C ¹¹	16	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	80.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	121	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹²	117	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	140	°C	ASTM D1525 ¹³
--	137	°C	ISO 306/B50
--	139	°C	ISO 306/B120
Ball Pressure Test ¹⁴ (125°C)	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			ASTM E831, ISO 11359-2
Flow: -40 to 40°C	5.7E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	6.0E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Flammability	Nominal Value	Unit	Test Method
NBS Smoke Density - Flaming, Dmax			ASTM E662
OSU peak heat release rate ¹⁵		kW/m ²	FAR 25.853
OSU total heat release ¹⁶		kW · min/m ²	FAR 25.853
Vertical Burn Test			FAR 25.853
Test a (60 s), passes at	2.4	sec	FAR 25.853
Test b (12 s), passes at	0.5	sec	FAR 25.853
Injection	Nominal Value	Unit	
Drying Temperature	107	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	12	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	
Rear Temperature	260 - 282	°C	
Middle Temperature	271 - 293	°C	
Front Temperature	282 - 304	°C	

Nozzle Temperature	277 - 299	°C
Processing (Melt) Temp	282 - 304	°C
Mold Temperature	71.1 - 104	°C
Back Pressure	0.345 - 0.689	MPa
Screw Speed	40 - 70	rpm
Vent Depth	0.025 - 0.076	mm

NOTE		
1.	5.0 mm/min	
2.	Type 1, 50mm/min	
3.	Type 1, 50mm/min	
4.	Type 1, 50mm/min	
5.	Type 1, 50mm/min	
6.	1.3 mm/min	
7.	2.0 mm/min	
8.	1.3 mm/min	
9.	80*10*4 sp=62mm	
10.	80*10*4	
11.	80*10*4	
12.	80*10*4 mm	
13.	标准 B (120°C/h), 载荷2 (50N)	
14.	Approximate maximum	
15.	5 minute test	
16.	2 minute test	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

