

ASI POLYETHYLENE CP 763-01 Natural

Low Density Polyethylene

A. Schulman Inc.

Message:

CP 763-01 Natural is an extruded, blow molding, and injection molding grade of low density polyethylene having good processability and heat sealability. This material meets the FDA Regulation 177.1520 for food contact applications.

General Information	
Features	Food Contact Acceptable
	Good Heat Seal
	Good Processability
Agency Ratings	FDA 21 CFR 177.1520
Appearance	Natural Color
Forms	Pellets
Processing Method	Blow Molding
	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.917	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	42		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	10.0	MPa	ASTM D638
Tensile Elongation ² (Break)	200	%	ASTM D638
Flexural Modulus - 1% Secant	207	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	92.0	°C	ASTM D1525
NOTE			
1.	51 mm/min		
2.	51 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

