

Braskem PP C780-07Z

Polypropylene Impact Copolymer

Braskem Europe GmbH

Message:

Braskem C780-07Z Polypropylene Resin is a high performance impact copolymer developed for injection moulding applications. Braskem C780-07Z Polypropylene Resin offers an excellent balance of mechanical properties and processability and an outstanding long term heat stability.

Applications for Braskem C780-07Z Polypropylene Resin:

Battery cases

Technical molded goods

Appliances

Automotive trim

Regulatory Information

Braskem C780-07Z Polypropylene Resin should comply with EU, No 10/2011. It is the responsibility of the manufacturers of food contact articles and industrial food packers to make sure the articles in their actual use are in compliance with the imposed migration requirements. The appropriate regulations should be consulted for more detailed information. Compliance letters can be obtained through the Braskem sales representative.

General Information			
Agency Ratings	EU No 10/2011		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, Injection Molded)	26.0	MPa	ISO 527-2
Tensile Strain (Yield, Injection Molded)	10	%	ISO 527-2
Flexural Modulus (Injection Molded)	1200	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-20°C, Injection Molded	6.0	kJ/m ²	
0°C, Injection Molded	7.5	kJ/m ²	
23°C, Injection Molded	12	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ¹ (0.45 MPa, Unannealed)	88.0	°C	ISO 75-2/B
Vicat Softening Temperature ²	151	°C	ISO 306/A
Accelerated Oven Ageing (150°C)	1800	hr	ISO 4577
NOTE			
1.	Injection Molded		
2.	Injection Molded		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

