

Starflam SF0067

Polyamide 12
Eurostar Engineering Plastics

Message:

Starflam SF0067 is a Halogen Free and Red Phosphorous Free Flame Retardant, Glass Fiber Reinforced, Polyamide 12 Injection Molding Resin

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
Additive	Flame retardancy		
Features	Phosphorus content, low (to none)		
	Halogen-free		
	Flame retardancy		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm ³	ASTM D792
shrinkage-Flow (24 hr)	0.20 - 0.40	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	101	MPa	ISO 527-2
Tensile Strain (Break)	3.3	%	ISO 527-2
Flexural Modulus	7800	MPa	ISO 178
Flexural Stress	140	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	40	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ¹ (1.8 MPa, Unannealed, 64.0 mm Span)	155	°C	ISO 75-2/Af
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.6 mm, E2P Measurement)	V-0		UL 94
Glow Wire Flammability Index (1.6 mm)	960	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	80	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	210 - 230	°C	
Middle Temperature	220 - 250	°C	
Front Temperature	220 - 250	°C	

Processing (Melt) Temp	220 - 260	°C
Mold Temperature	60 - 90	°C
NOTE		
1.	80x10x4 mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

