

POCAN® B 1505 000000

Polybutylene Terephthalate

LANXESS GmbH

Message:

PBT, non-reinforced, injection molding, extrusion

General Information			
UL YellowCard	E245249-100603183		
Processing Method	Extrusion		
	Injection Molding		
Multi-Point Data	Creep Modulus vs. Time (ISO 11403-1)		
	Isochronous Stress vs. Strain (ISO 11403-1)		
	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
	Shear Modulus vs. Temperature (ISO 11403-1)		
	Specific Volume vs Temperature (ISO 11403-2)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
	1.31		
Density (23°C)	1.31	g/cm ³	ISO 1183
Apparent Density	0.80	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	16.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 2577
Across Flow : 250°C, 2.00 mm ¹	2.1	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.20	%	
Flow : 250°C, 2.00 mm ³	2.1	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.20	%	
Water Absorption			ISO 62
	0.50		
Saturation, 23°C	0.50	%	

0.20

Equilibrium, 23°C, 50% RH

0.20

%

Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	120	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
23°C	2470	MPa	ASTM D638
23°C	2700	MPa	ISO 527-2/1
Tensile Stress			
Yield, 23°C	60.0	MPa	ISO 527-2/50
Break, 23°C	33.8	MPa	ASTM D638
Tensile Strain			
Yield, 23°C	9.0	%	ISO 527-2/50
Break, 23°C	29	%	ASTM D638
Nominal Tensile Strain at Break (23°C)	> 15	%	ISO 527-2/50
Tensile Creep Modulus			ISO 899-1
1 hr	2200	MPa	
1000 hr	1300	MPa	
Flexural Modulus			
23°C	2090	MPa	ASTM D790
23°C ⁵	2650	MPa	ISO 178/A
Flexural Strength			
23°C	85.5	MPa	ASTM D790
3.5% Strain, 23°C	80.0	MPa	ISO 178/A
23°C ⁶	90.0	MPa	ISO 178/A
Flexural Strain at Flexural Strength (23°C) ⁷	6.0	%	ISO 178/A
Halving Interval			IEC 60216
Electric Strength	12.6	°C	
Tensile Impact Strength	12.0	°C	
Tensile Strength	12.6	°C	
Temperature Index			IEC 60216
Electric Strength, 20000 hr	150	°C	
Tensile Impact Strength, 20000 hr	135	°C	
Tensile Strength, 20000 hr	150	°C	
Burning Behavior ⁸	passed		ISO 3795
Electrolytical Corrosion (23°C)	A 1		IEC 60426
ISO Shortname	PBT, GHMR, 11-030		ISO 7792

0.0 to 0.020

Residual Moisture Content	0.0 to 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	180	kJ/m ²	
23°C	No Break		
Notched Izod Impact Strength			ISO 180/1A
-40°C	< 10	kJ/m ²	
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	150	kJ/m ²	
23°C	No Break		
Multi-Axial Instrumented Impact Energy			ISO 6603-2
-30°C	32.0	J	
23°C	22.0	J	
Multi-Axial Instrumented Impact Peak Force			ISO 6603-2
-30°C	5190	N	
23°C	3650	N	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	150	°C	ISO 75-2/B
1.8 MPa, Unannealed	60.0	°C	ISO 75-2/A
8.0 MPa, Unannealed	45.0	°C	ISO 75-2/C
Ball Pressure Test (190°C)	Pass		IEC 60695-10-2
Melting Temperature ⁹	225	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow : 23 to 55°C	1.2E-4	cm/cm/°C	
Transverse : 23 to 55°C	1.2E-4	cm/cm/°C	
Thermal Conductivity (23°C)	0.25	W/m/K	ISO 8302
RTI Elec	140	°C	UL 746
RTI Imp	125	°C	UL 746
RTI Str	140	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Electric Strength (23°C, 1.00 mm)	30	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250

23°C, 100 Hz	3.40		
23°C, 1 MHz	3.20		
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	HB		
1.60 mm	HB		
Glow Wire Flammability Index (2.00 mm)	750	°C	IEC 60695-2-12
Oxygen Index ¹⁰	24	%	ISO 4589-2
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
	4.0 to 8.0		
Drying Time - Circulation Dryer	4.0 to 8.0	hr	
Processing (Melt) Temp	250 to 260	°C	
Mold Temperature	80.0 to 100	°C	
NOTE			
1.	60x60x2mm, 80°C MT, 600 bar		
2.	60x60x2mm		
3.	60x60x2mm, 80°C MT, 600 bar		
4.	60x60x2mm		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	2 mm/min		
8.	US-FMVSS302		
9.	10°C/min		
10.	Procedure A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT